

# PROTINFLUX 1003

Classification selon norme : EN 9454-1 : 2016 3.1.1.4

ISO 9001  
ISO 14001  
BUREAU VERITAS  
Certification



## APPLICATION FIELD

PROTINFLUX 1003 is formulated for brazing metals (except Aluminum and its alloys)

This is a universal flux suitable for all application fields.

Not suitable for brazing/welding of drinking-water pipes.

## CHARACTERISTICS, CHEMICOPHYSICAL PROPERTIES

Thick Liquid from mineral salts

Color: Uncolored

Density: 1.3-1.5

Application temperature: 240-450°C

## DIRECTION FOR USE

Heating method: soldering iron, torch, or flame

Use with tin braze alloys.

First, check that surfaces are cleaned.

Apply flux with a brush equally on surfaces to join.

Residues easily removed with water or wet cloth.

## PACKAGING

Plastic pot of 320 ml.

## MISCELLANEOUS

All active materials are in compliance with REACH.

Refer to MSDS (Health and Safety data sheet) – available on demand.

Note: The contents of this data sheet result from our knowledge and experience of the product, given as an indication but does not engage our responsibility for each particular case.