



Decapzinc 1088

ISO 9001
ISO 14001
BUREAU VERITAS
Certification



APPLICATION FIELD

The product is formulated to remove polymer coating on treated-zinc plates.

We recommend running a test on a small zone or on a sample to ensure product efficiency according to the type of coating to strip.

CHARACTERISTICS, CHEMICO-PHYSICAL PROPERTIES

Stripping liquid solvent

Density: 1.02-1.05

DIRECTION FOR USE

Use pure:

- 1- Apply Decapzinc 1088 with a brush directly on the surface to treat.
- 2- Leave on for at least 2 or 3 minutes.
- 3- Microbubbles and/or blister will appear on the surface – this is normal
- 4- Remove the layer with a duster or a wire brush. Ensure that liner is removed to ensure the efficiency of brazing flux. Repeat if necessary.

Decapzinc 1088 should be used with our Protinflux 1082.

PACKAGING

Plastic pot of 320 ml.

MISCELLANEOUS

All active materials are in compliance with REACH.

Refer to MSDS (Health and Safety data sheet) – available on demand.

Note: The contents of this data sheet result from our knowledge and experience of the product, given as an indication but does not engage our responsibility for each particular case.