

COBOR 1052

Classification selon norme: EN1045-FH10



APPLICATION FIELD

Flux Cobor 1052 is a powder version of Cobor 1049.

This pickling powder is recommended for braze-welding operations of carburized steels, copper, and nickel alloys.

CHARACTERISTICS, CHEMICO-PHYSICAL PROPERTIES

White powder

Calibrated granulometry

Application temperature: 550-800°C

DIRECTION FOR USE

Heating method: Induction.

It can be used:

- · as powder
- · as paste: by mixing with water
- with the hot-rodding technique: by dipping a warm brazing rod into the powder.

Residues can be removed by soaking in cold water or by brushing.

PACKAGING

Plastic pot of 500 g or 1 Kg Drum of 25 Kg

MISCELLANEOUS

All active materials are in compliance with REACH.

Refer to MSDS (Health and Safety data sheet) – available on demand.

Note: The contents of this data sheet result from our knowledge and experience of the product, given as an indication but does not engage our responsibility for each particular case.

www.stts-flux.com